

OPADRY[®] Enteric

Product Information

Formulated for Solvent Coating

Hypromellose Phthalate (HPMC-P):

Preparation & Use Guidelines


Opadry Enteric is a family of fully-formulated, delayed release coating systems for solid oral dosage forms, applied by hydro-alcoholic processing techniques.

MATERIALS

- Opadry Enteric film coating system
- Hydro-alcoholic solvent system (see note below)

EQUIPMENT

- Variable-speed mixer capable of producing and maintaining a vortex.
- Propeller stirrer. For optimum mixing, utilize a propeller with a diameter equivalent to 1/3-1/2 of the diameter of the mixing vessel (Figure 1).
- Mixing vessel suitable to contain a liquid volume 15-25% greater than the total suspension being prepared. The liquid height and vessel diameter should be equal.



SOLVENT SELECTION

The recommended solvent system is ethanol/ water mixture. Recommended alcoholic content in the solvent mixture is 80% by weight.

Note: Opadry Enteric, HPMC-P does not dissolve in 100% ethanol or 100% water. A hydro-alcoholic solvent system is necessary

Hydro-alcoholic Solvent System

Dispersion Viscosity (cp)

Ethanol : water (8:2)

37

Note: The choice of solvents depends on specific country regulations and local policies. Follow all solvent manufacturer recommendations and associated Material Safety Data Sheets for the safe handling practices for your solvent of choice.

MIXING PROCEDURE

- Determine the amount of Opadry Enteric and solvents required; based on the quantity of tablets to be coated, target coating weight, and solvent system used.
- Weigh the solvents into the mixing vessel.
- Using a propeller stirrer, stir the solvent to form a vortex.
- Weigh the Opadry Enteric and add to the center of the liquid vortex in a slow steady stream, avoiding clumping and maintaining a vortex.
- After all the Opadry Enteric has been added, reduce the stirrer speed until the vortex is just eliminated.
- Continue stirring for at least 45 minutes after which time the dispersion will be ready for coating.
- Ensure the dispersion is gently stirred during the coating process.

USE GUIDELINES

- Opadry Enteric can be reconstituted up to 12.5% solids, using a hydro-alcoholic solvent system.
- The coating system can be pigmented to meet marketing requirements and is also available as a translucent enteric coating system.
- Recommended coating weight gains of Opadry Enteric are up to 8-10% for delayed release performance, depending on the physicochemical properties of the core tablets. The actual weight gain required for a specific application should be determined by conducting laboratory coating trials.
- A sub-coat may be required to separate the active pharmaceutical ingredient from the enteric polymer, or to strengthen the dosage form prior to enteric coating. A recommended sub-coat is Opadry 03K19229 Clear. The sub-coat can be applied using either an aqueous or an organic solvent system.
- A clear Opadry top-coat is recommended at 1-2% weight gain to prevent the tablets from sticking to each other upon bulk storage.

CLEAN UP GUIDELINES

For best results, clean equipment shortly after the end of the coating run.

- Opadry Enteric residue remaining on the coating equipment can easily be removed using a mild (greater than pH 6.0) sodium bicarbonate solution. Sodium bicarbonate (NaHCO₃) is regarded as an essentially nontoxic and non-irritant material. Additionally, it is GRAS listed and has compendia status within the USP, BP, JP and PHEur.
- Coating pans can be cleaned with a solution of NaHCO₃ and deionized water. If equipped, fill the pan reservoir with cleaning solution and allow the pan to rotate through the solution for 30 minutes.
- Spray equipment (guns and hoses) should be disassembled and can be soaked in the cleaning solution for 30 minutes.
- When cleaning spray guns, it is important to make sure the passages are free of residual coating material that can block the orifice and restrict flow. A thin soft brush or swab can be passed through the tip of the gun to ensure all the coating material is removed. Avoid using hard substances because these can damage the gun parts.
- All equipment should be rinsed with deionized water after cleaning

The information contained herein, to the best of Colorcon, Inc.'s knowledge is true and accurate. Any recommendations or suggestions of Colorcon, Inc. with regard to the products provided by Colorcon, Inc. are made without warranty, either implied or expressed, because of the variations in methods, conditions and equipment which may be used in commercially processing the products, and no such warranties are made for the suitability of the products for any applications that you may have disclosed. Colorcon, Inc. shall not be liable for loss of profit or for incidental, special or consequential loss or damages.

Colorcon, Inc. makes no warranty, either expressed or implied, that the use of the products provided by Colorcon, Inc., will not infringe any trademark, trade name, copyright, patent or other rights held by any third person or entity when used in the customer's application.

For more information, contact your Colorcon representative or call:

North America	Europe/Middle East/Africa	Latin America	India	China
+1-215-699-7733	+44-(0)-1322-293000	+54-1-5556-7700	+91-832-6727373	+86-21-61982300

You can also visit our website at www.colorcon.com



© BPSI Holdings LLC, 2019.

The information contained in this document is proprietary to Colorcon and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holdings, LLC.

Pi_opadry_enteric_HPMCP_prep_&use_ver2_04_2019